



Timeless natural hues

# PANAGET

manufacture française de parquet  
DEPUIS 1929



N° 1021455

## FLAMED BEECH SATIN, HERRINGBONE 139 TONGUE&GROOVE / 14 MM

### Characteristics

**Specie:** Beech **Origin:** France

**Grade:** - Flamed red wood, light and dark wood, knots, all peculiarities accepted.

**Finish: Satin** - unbrushed, satin lacquered / Ecostrong satin lacquer - Gloss: 28/32

### Design

Engineered single plank herringbone made under the patent EN 13489  
Tongue&Groove

### Description

**Width:** 139 mm  
**Length:** 800 mm  
**Thickness:** 14 mm  
**Top layer:** 3.4 mm  
**Core:** plywood  
**Counterbalance:** unrolled wood  
**Profile:** 4 bevels

### Packaging

**sqm/pack:** 2.22  
**Pack/pallet:** 32  
**sqm/pallet:** 71.04  
**Weight/sqm:** 7.4 kg  
**Weight/pallet:** 525.7 kg



### Installation method





Floating glued  
installation under the  
patent DTU 51.11



Glue down installation  
under the patent DTU 51.2



Collage en plein avec presto PM  
uniuement.



PANAGET - 3 rue d'Orgères - 35230 Bourgbarré - FRANCE  
tel: +33 (0)2 99 05 77 77 // fax: +33 (0)2 99 57 73 55 // [www.panaget.com](http://www.panaget.com)



# DECLARATION OF PERFORMANCE

## N° 1021455

**Unique identification code of product-type:** Herringbone 139 Tongue&Groove, 14 mm, Beech

**Intended use/es:** Engineered single plank made under the patent EN 13489

Floating glued installation under the patent DTU 51.11

**Manufacturer:** PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

**System/s of Assessment and Verification of Constancy of Performance:** n°4

**Harmonised standard:** EN 14342 : 2013

### Declared performances:

Essential features	Performances	Appropriate Technical Documentation and/or Specific Technical Documentation
Reaction of fire	Dfl-s1	EN 14342 : 2013
Features for this classification:		
- Average minimum density (Kg/m <sup>3</sup> )	500	
- Average thickness (mm)	14	
- Intended use, fitting mode	Floating fit	
Formaldehyde emission	E1	EN 717-1
Content of pentachlorophenol	PCP ≤ 5 ppm	-
Release of other dangerous substances:		ISO 16000
- VOC* emissions (Decree No 2011-321)	Class A+	
- CMR 1&2** emissions (Decree No DEVP0910046A)	< 1µg/m <sup>3</sup>	
Breaking strength	N/A	-
Slipperiness	N/A	-
Thermal conductivity (W/m.K)	0.13	EN 14342 / Chapter 4.7
Thermal resistance (m <sup>2</sup> .K/W)	0.108	
Biological sustainability	Class 1	EN 335
RE2020 - Building Carbon Index	3 kg.CO <sub>2</sub> /m <sup>2</sup>	-
FDES 2022 - Life Cycle impact assessment	8.6 kg éq. CO <sub>2</sub> /m <sup>2</sup>	-

N/A : Not Applicate

\*VOC: Volatile Organic Compounds

\*\*CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category.

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011 under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole FRANÇOIS - Executive Director

Bourgbarré, January 27th 2025

**Carole FRANÇOIS**

