



Subtle greys N° 1007655

# FRENCH OAK ZENITUDE-ORIGINE FLANELLE, HERRINGBONE 139 TONGUE&GROOVE / 14 MM

# Characteristics

Specie: French oak Origin: France

**Grade: Zenitude-Origine** - Light and dark wood, black knots, filled knots, partially opened knots, traces of discolouration, cracks, splits, heartwood, sapwood. Grade with all peculiarities of the wood without limitation. The size of the knots is proportional to the width of the planks. Origine, characterized by two aged bevels on the lengths.

Finish: Flanelle - brushed, grey-brown matt oiled brun / Oil - Gloss: 5/8

For oiled wood floors, apply a thin coat of Panaget maintenance oil right after installation. Please refer to our maintenance guide. While we take the greatest care in manufacturing our flooring, there can sometimes be slight variations in colouring. So it's important to factor in margin 2-5% more than the actual you're covering. This means you won't run out of planks and will be sure to enjoy beautiful finished product.

## Design

Engineered single plank herringbone made under the patent EN 13489 Tongue&Groove





# Description

Width: 139 mm Length: 800 mm Thickness: 14 mm Top layer: 3.4 mm Core: plywood

Counterbalance: unrolled wood

**Profile:** 2 bevels vieillis

# Packaging

sqm/pack: 2.22 Pack/pallet: 32 sqm/pallet: 71.04 Weight/sqm: 7.4 kg Weight/pallet: 525.7 kg



# Installation method



Floating glued installation under the patent DTU 51.11



Glue down installation under the patent DTU 51.2



Floating installation gluing TG using plastic DPM and Isol 20 or fully glue down using Presto PM















# **DECLARATION OF PERFORMANCE**

N° 1007655

Unique identification code of product-type: Herringbone 139 Tongue&Groove, 14 mm, French oak

Intented use/es: Engineered single plank made under the patent EN 13489

Floating glued installation under the patent DTU 51.11

Manufacturer: PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

System/s of Assessment and Verification of Constancy of Performance: n°4

Harmonised standard: EN 14342: 2013

#### **Declared performances:**

Essential features	Performances	Appropriate Technical Documentation and/or Specific Technical Documentation
Reaction of fire	Dfl-s1	
Features for this classification:		
- Average minimum density (Kg/m³)	500	EN 14342 : 2013
- Average thickness (mm)	14	
- Intented use, fitting mode	Floating fit	
Formaldehyde emission	E1	EN 717-1
Content of pentachlorophenol	PCP ≤ 5 ppm	-
Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree No DEVP0910046A)	Class A+ < 1µg/m³	ISO 16000
Breaking strength	N/A	-
Slipperiness	N/A	-
Thermal conductivity (W/m.K)	0.13	EN 14342 / Chapter 4.7
Thermal resistance (m².K/W)	0.108	
Biological sustainability	Class 1	EN 335
RE2020 - Building Carbon Index	3 kg.CO <sub>2</sub> /m <sup>2</sup>	-
FDES 2022 - Life Cycle impact assessment	8.6 kg éq. CO <sub>3</sub> /m²	-

N/A: Not Applicate

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011 under the sole responsability of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole FRANÇOIS - Executive Director

Bourgbarré, January 27th 2025

**Carole FRANÇOIS** 

3 rue d'Orgères - 35230 Bourgbarré - FRANCE / tel: +33 (0)2 99 05 77 77 - fax: +33 (0)2 99 57 73 55 Entreprise dont le système qualité a été certifié ISO 9001 par Bureau Veritas Certification. SAS au capital de 4 957 200 € - RCS Rennes B 402 853 220 - Siret : 402 853 220 000 34 - APE : 1622 Z - n° TVA : FR 0640 2853220

www.panaget.com

<sup>\*</sup>VOC: Volatile Organic Compounds

<sup>\*\*</sup>CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category.