



Timeless natural hues

N° 1022059

FRENCH OAK ZENITUDE NOISETTE, HERRINGBONE TONGUE&GROOVE / 12 MM

Characteristics

Specie: French oak **Origin:** France

Grade: Zenitude - Light and dark wood, black knots, filled knots, partially opened knots, traces of discolouration, cracks, splits, heartwood, sapwood. Grade with all peculiarities of the wood without limitation. The size of the knots is proportional to the width of the planks.

Finish: Noisette - brushed, light brown matt lacquered / Ecostrong matt lacquer - Gloss: 4/6

Design

Engineered single plank herringbone made under the patent EN 13489
 Tongue&Groove



Description

Width: 90 mm
Length: 590 mm
Thickness: 12 mm
Top layer: 2.5 mm
Core: HDF*
Counterbalance: unrolled wood
Profile: 4 bevels

*High Density Fiber board

Packaging

sqm/pack: 1.91
Pack/pallet: 32
sqm/pallet: 61.12
Weight/sqm: 9.9 kg
Weight/pallet: 605.1 kg



Installation method



Floating glued
 installation under the
 patent DTU 51.11




Glue down installation
 under the patent DTU 51.2



Floating installation gluing TG
 using plastic DPM and Isol 20 or
 fully glue down using Presto PM



Fully glue down Presto PM



DECLARATION OF PERFORMANCE

N° 1022059



Unique identification code of product-type: Herringbone 90 Tongue&Groove, 12 mm, French oak

Intended use/es: Engineered single plank made under the patent EN 13489

Floating glued installation under the patent DTU 51.11

Manufacturer: PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

System/s of Assessment and Verification of Constancy of Performance: n°4

Harmonised standard: EN 14342 : 2013

Declared performances:

| Essential features | Performances | Appropriate Technical Documentation and/or Specific Technical Documentation | |
|---|--|---|----------|
| Reaction of fire | Dfl-s1 | EN 14342 : 2013 | |
| Features for this classification: - Average minimum density (Kg/m ³) - Average thickness (mm) - Intended use, fitting mode | 500 12 Floating fit | | |
| Formaldehyde emission | E1 | | EN 717-1 |
| Content of pentachlorophenol | PCP ≤ 5 ppm | | - |
| Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree No DEVP0910046A) | Class A+ < 1µg/m ³ | ISO 16000 | |
| Breaking strength | N/A | - | |
| Slipperiness | N/A | - | |
| Thermal conductivity (W/m.K) | 0.15 | EN 14342 / Chapter 4.7 | |
| Thermal resistance (m ² .K/W) | 0.080 | | |
| Biological sustainability | Class 1 | EN 335 | |
| RE2020 - Building Carbon Index | 3 kg.CO ₂ /m ² | - | |
| FDES 2022 - Life Cycle impact assessment | 8.6 kg éq. CO ₂ /m ² | - | |

N/A : Not Applicate

*VOC: Volatile Organic Compounds

**CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category.

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011 under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole FRANÇOIS - Executive Director

Bourgbarré, January 27th 2025
Carole FRANÇOIS

