



Elegant browns

PANAGET

manufacture française de parquet
DEPUIS 1929



N° 1014176

FRENCH OAK AUTHENTIC CUIR, DIVA 139 CLICK / 12 MM

Characteristics

Species: French oak **Origin:** France

Grade: Authentic - Light and dark wood, black knots, filled knots, partially opened knots, traces of discolouration, black marks, cracks. The size of the knots is proportional to the width of the planks.

Finish: Cuir - brushed, old leather-tone matt oiled / Oil - Gloss: 4/8

For oiled wood floors, apply a thin coat of Panaget maintenance oil right after installation. Please refer to our maintenance guide.

Design

Engineered wide single plank made under the patent EN 13489

Click made under Unilin patent n°EP1640530



Description

Width: 139 mm

Length: 495 to 1992 mm

Thickness: 12 mm

Top layer: 2.5 mm

Core: HDF*

Counterbalance: unrolled wood

Profile: 4 bevels

*High Density Fiber board

Packing

Sqm/pack: 1.38

Pack/pallet: 65

Sqm/pallet: 89,70

Weight/sqm: 9.9 kg

Weight/pallet: 888.0 kg

Installation method



Glue-free floating under
the patent DTU 51.11




Glue down installation
under the patent DTU 51.2




Floating installation using
plastic DPM and Iso 20 or fully
glue down using Presto PM



Fully glue down using
Presto PM



* Emissions of volatile substances which could be toxic if inhaled. These are rated on scale from A+ (very low) to C (high).



PANAGET - 3 rue d'Orgères - 35230 Bourgarré - FRANCE
tel: +33 (0)2 99 05 77 77 // fax: +33 (0)2 99 57 73 55 // www.panaget.com

DECLARATION OF PERFORMANCE

N° 1014176



Unique identification code of the product-type: Diva 139 Click, 12 mm, French oak

Intended use/es: Engineered single plank made under the patent EN 13489

Glue-free floating under the patent DTU 51.11

Manufacturer: PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

System/s of Assessment and Verification of Constancy of Performance: n°4

Harmonised standard: EN 14342 : 2013

Declared performances:

Essential features	Performances	Appropriate Technical Documentation and/or Specific Technical Documentation
Reaction of fire	Dfl-s1	EN 14342 : 2013
Features for this classification: - Average minimum density (Kg/m ³)	500	
- Average thickness (mm)	12	
- Intended use, fitting mode	Floating fit	
Formaldéhyde emission	E1	EN 717-1
Content of pentachlorophenol	PCP ≤ 5 ppm	-
Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree No DEVP0910046A)	Class A+ < 1 µg/m ³	ISO 16000
Breaking strength	N/A	-
Slipperiness	N/A	-
Thermal conductivity (W/m.K)	0,15	EN 14342 / Chapitre 4.7
Thermal resistance (m ² .K/W)	0,08	
Biological sustainability	Class 1	EN 335
RE2020 - Building Carbon Index	3 kg.CO ₂ /m ²	-
FDES 2022 - Life Cycle impact assessment	8,6 kg éq. CO ₂ /m ²	-

N/A : Not Applicate

*VOC: Volatile Organic Compounds

**CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011 under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole FRANÇOIS - Executive Director

Bourgbarré, 15 december 2023

Carole FRANÇOIS

