



# PANAGET

manufacture française de parquet  
DEPUIS 1929



N° 1005774

Timeless natural hues

## FRENCH OAK CLASSIC BOIS FLOTTÉ, DIVA 139 CLICK / 12 MM

### Characteristics

**Species:** French oak **Origin:** France

**Grade:** Classic - Light and dark wood, black knots, medular rays and traces of discolouration.

**Finish:** Bois flotté - brushed, matt lacquered with unfinished aspect / Ecostrong lacquer - Gloss: 4/6

### Design

Engineered wide single plank made under the patent EN 13489  
Click made under Unilin patent n°EP1640530



### Description

**Width:** 139 mm  
**Length:** 495 to 1992 mm  
**Thickness:** 12 mm  
**Top layer:** 2.5 mm  
**Core:** HDF\*  
**Counterbalance:** unrolled wood  
**Profile:** 4 bevels

\*High Density Fiber board

### Packing

**Sqm/pack:** 1.38  
**Pack/pallet:** 65  
**Sqm/pallet:** 89,70  
**Weight/sqm:** 9.9 kg  
**Weight/pallet:** 888.0 kg

### Installation method



Glue-free floating under  
the patent DTU 51.11



Glue down installation  
under the patent DTU 51.2




Floating installation using  
plastic DPM and Isol 20 or fully  
glue down using Presto PM



Fully glue down using  
Presto PM



\* Emissions of volatile substances which could be toxic if inhaled. These are rated on scale from A+ (very low) to C (high).



PANAGET - 3 rue d'Orgères - 35230 Bourgarré - FRANCE  
tel: +33 (0)2 99 05 77 77 // fax: +33 (0)2 99 57 73 55 // [www.panaget.com](http://www.panaget.com)

# DECLARATION OF PERFORMANCE

N° 1005774



**Unique identification code of the product-type:** Diva 139 Click, 12 mm, French oak

**Intended use/es:** Engineered single plank made under the patent EN 13489

Glue-free floating under the patent DTU 51.11

**Manufacturer:** PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

**System/s of Assessment and Verification of Constancy of Performance:** n°4

**Harmonised standard:** EN 14342 : 2013

## Declared performances:

Essential features	Performances	Appropriate Technical Documentation and/or Specific Technical Documentation
Reaction of fire	Dfl-s1	EN 14342 : 2013
Features for this classification: - Average minimum density (Kg/m <sup>3</sup> )	500	
- Average thickness (mm)	12	
- Intended use, fitting mode	Floating fit	
Formaldéhyde emission	E1	EN 717-1
Content of pentachlorophenol	PCP ≤ 5 ppm	-
Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree No DEVP0910046A)	Class A+ < 1 µg/m <sup>3</sup>	ISO 16000
Breaking strength	N/A	-
Slipperiness	N/A	-
Thermal conductivity (W/m.K)	0,15	EN 14342 / Chapitre 4.7
Thermal resistance (m <sup>2</sup> .K/W)	0,08	
Biological sustainability	Class 1	EN 335
RE2020 - Building Carbon Index	3 kg.CO <sub>2</sub> /m <sup>2</sup>	-
FDES 2022 - Life Cycle impact assessment	8,6 kg éq. CO <sub>2</sub> /m <sup>2</sup>	-

N/A : Not Applicate

\*VOC: Volatile Organic Compounds

\*\*CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011 under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole FRANÇOIS - Executive Director

Bourgbarré, 15 december 2023

**Carole FRANÇOIS**

