



Timeless natural hues

N° 1021882

## FRENCH OAK ZENITUDE AMANDE, DIVA 184 CLICK / 12 MM

### Characteristics

**Species:** French oak **Origin:** France

**Grade: Zenitude** - Light and dark wood, black knots, filled knots, partially opened knots, traces of discolouration, cracks, splits, heartwood, sapwood. Grade with all peculiarities of the wood. The size of the knots is proportional to the width of the planks.

**Finish: Amande** - natural brushed, slightly ceruse oiled / Oil - Gloss: 5/8

For oiled wood floors, apply a thin coat of Panaget maintenance oil right after installation. Please refer to our maintenance guide.

### Design

Engineered extra-wide single plank made under the patent EN 13489

Click system under Unilin patent n°EP1640530

### Description

**Width:** 184 mm

**Length:** 495 to 1992 mm

**Thickness:** 12 mm

**Top layer:** 2.5 mm

**Core:** HDF\*

**Counterbalance:** unrolled wood

**Profile:** 4 bevels

\*High Density Fiber Board

### Packing

**Sqm/pack:** 2.20

**Pack/pallet:** 40

**Sqm/pallet:** 88,00

**Weight/sqm:** 9.9 kg

**Weight/pallet:** 1 916,6 kg



### Installation method



Glue-free floating under the patent DTU 51.11





Glue down installation under the patent DTU 51.2



Floating installation using plastic DPM and Isol 20 or fully glue down using Presto PM



Fully glue down using Presto PM



# DECLARATION OF PERFORMANCE

## N° 1021882



**Unique identification code of the product-type:** Diva 184 Click, 12 mm, French oak

**Intended use/es:** Engineered single plank made under the patent EN 13489

Glue-free floating under the patent DTU 51.11

**Manufacturer:** PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

**System/s of Assessment and Verification of Constancy of Performance:** n°4

**Harmonised standard:** EN 14342 : 2013

### Declared performances:

Essential features	Performances	Appropriate Technical Documentation and/or Specific Technical Documentation
Reaction of fire	Dfl-s1	EN 14342 : 2013
Features for this classification: - Average minimum density (Kg/m <sup>3</sup> )	500	
- Average thickness (mm)	12	
- Intended use, fitting mode	Floating fit	
Formaldéhyde emission	E1	EN 717-1
Content of pentachlorophenol	PCP ≤ 5 ppm	-
Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree n° DEVP0910046A)	Class A+ < 1 µg/m <sup>3</sup>	ISO 16000
Breaking strength	N/A	-
Slipperiness	N/A	-
Thermal conductivity (W/m.K)	0,15	EN 14342 / Chapter 4.7
Thermal resistance (m <sup>2</sup> .K/W)	0,08	
Biological sustainability	Class 1	EN 335
RE2020 - Building Carbon Index	3 kg.CO <sub>2</sub> /m <sup>2</sup>	-
FDES 2022 - Life Cycle impact assessment	8.6 kg éq. CO <sub>2</sub> /m <sup>2</sup>	-

N/A : Not Applicate

\*VOC: Volatile Organic Compounds

\*\*CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regluation (EU) No 305/2011 under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole François - Executive Director

Bourgbarré, 15 december 2023  
**Carole FRANÇOIS**

