



Timeless natural hues

N° 1019713

## FLAMED BEECH NATURAL OIL, DIVA 139 CLICK / 14 MM

### Characteristics

**Specie:** Beech **Origin:** France

**Grade:** - Flamed red wood, light and dark wood, knots, all peculiarities accepted.

**Finish: Natural oil** - brushed, matt oiled / Oil - Gloss: 5/8

For oiled wood floors, apply a thin coat of Panaget maintenance oil right after installation.

### Design

Engineered wide single plank made under the patent EN 13489

Click made under Unilin patent n°EP1640530



### Description

**Width:** 139 mm

**Length:** 495 to 1992 mm

**Thickness:** 14 mm

**Top layer:** 3.4 mm

**Core:** HDF\*

**Counterbalance:** unrolled wood

**Profile:** 4 bevels

\*High Density Fiber board

### Packaging

**sqm/pack:** 1.38

**Pack/pallet:** 55

**sqm/pallet:** 75.90

**Weight/sqm:** 11.6 kg

**Weight/pallet:** 880.4 kg



### Installation method





Glue-free floating under  
the patent DTU 51.11



Glue down installation  
under the patent DTU 51.2



Collage en plein avec presto PM  
uniquement.



# DECLARATION OF PERFORMANCE

## N° 1019713



**Unique identification code of product-type:** Diva 139 Click, 14 mm, Beech

**Intended use/es:** Engineered single plank made under the patent EN 13489  
Glue-free floating under the patent DTU 51.11

**Manufacturer:** PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

**System/s of Assessment and Verification of Constancy of Performance:** n°4

**Harmonised standard:** EN 14342 : 2013

### Declared performances:

| Essential features  | Performances                               | Appropriate Technical Documentation and/or Specific Technical Documentation |
|---|--|---|
| Reaction of fire  | Dfl-s1                                     | EN 14342 : 2013   |
| Features for this classification:<br>- Average minimum density (Kg/m <sup>3</sup> )<br>- Average thickness (mm)<br>- Intended use, fitting mode | 500<br>14<br>Floating fit                  |   |
| Formaldehyde emission   | E1   |   |
| Content of pentachlorophenol  | PCP ≤ 5 ppm                                | -   |
| Release of other dangerous substances:<br>- VOC* emissions (Decree No 2011-321)<br>- CMR 1&2** emissions (Decree No DEVP0910046A)               | Class A+<br>< 1µg/m <sup>3</sup>           | ISO 16000   |
| Breaking strength   | N/A  | -   |
| Slipperiness  | N/A  | -   |
| Thermal conductivity (W/m.K)  | 0.15                                       | EN 14342 / Chapter 4.7  |
| Thermal resistance (m <sup>2</sup> .K/W)  | 0.093                                      |   |
| Biological sustainability   | Class 1                                    | EN 335  |
| RE2020 - Building Carbon Index  | 3 kg.CO <sub>2</sub> /m <sup>2</sup>       | -   |
| FDES 2022 - Life Cycle impact assessment  | 8.6 kg éq. CO <sub>2</sub> /m <sup>2</sup> | -   |

N/A : Not Applicate

\*VOC: Volatile Organic Compounds

\*\*CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category.

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011 under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole FRANÇOIS - Executive Director

Bourgbarré, January 27th 2025  
**Carole FRANÇOIS**

