

Subtle greys

PANAGET

manufacture française de parquet
DEPUIS 1929



N° 1021038

FRENCH OAK AUTHENTIC CAFÉ CRÈME HIGH TRAFFIC, DIVA 139 CLICK / 14 MM

Characteristics

Specie: French oak **Origin:** France

Grade: Authentic - Light and dark wood, black knots, filled knots, partially opened knots, traces of discolouration, black marks, cracks. This size of the knots is proportional to the width of the planks.

Finish: Café crème High Traffic - brushed, coffee latte tone matt lacquered / Matt lacquer High Traffic - Gloss: 4

Design

Engineered wide single plank made under the patent EN 13489
Click made under Unilin patent n°EP1640530



Description

Width: 139 mm
Length: 495 to 1992 mm
Thickness: 14 mm
Top layer: 3.4 mm
Core: HDF*
Counterbalance: unrolled wood
Profile: 4 bevels

*High Density Fiber board

Packaging

sqm/pack: 1.38
Pack/pallet: 55
sqm/pallet: 75.90
Weight/sqm: 11.6 kg
Weight/pallet: 880.4 kg



if installation and maintenance rules are followed

Installation method



Glue-free floating under the patent DTU 51.11




Glue down installation under the patent DTU 51.2




Floating installation using plastic DM and Isol 20 or fully glue down using Presto PM



Fully glue down Presto PM



*Emissions of volatile substances which could be toxic if inhaled. These are rated on scale from A+ (very low) to C (high).





DECLARATION OF PERFORMANCE

N° 1021038

Unique identification code of product-type: Diva 139 Click, 14 mm, French oak

Intended use/es: Engineered single plank made under the patent EN 13489

Glue-free floating under the patent DTU 51.11

Manufacturer: PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

System/s of Assessment and Verification of Constancy of Performance: n°4

Harmonised standard: EN 14342 : 2013

Declared performances:

Essential features	Performances	Appropriate Technical Documentation and/or Specific Technical Documentation	
Reaction of fire	Dfl-s	EN 14342 : 2013	
Features for this classification: - Average minimum density (Kg/m ³) - Average thickness (mm) - Intended use, fitting mode	500 14 Floating fit		
Formaldehyde emission	E1		EN 717-1
Content of pentachlorophenol	PCP ≤ 5 ppm		-
Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree No DEVPO910046A)	Class A+ < 1µg/m ³	ISO 16000	
Breaking strength	N/A	-	
Slipperiness	N/A	-	
Thermal conductivity (W/m.K)	0.15	EN 14342 / Chapter 4.7	
Thermal resistance (m ² .K/W)	0.093		
Biological sustainability	Class 1	EN 335	
RE2020 - Building Carbon Index	3 kg.CO ₂ /m ²	-	
FDES 2022 - Life Cycle impact assessment	8.6 kg éq. CO ₂ /m ²	-	

N/A : Not Applicable


*VOC: Volatile Organic Compounds

**CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category.

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011 under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole FRANÇOIS - Executive Director

Bourgbarré, January 27th 2025
Carole FRANÇOIS



3 rue d'Orgères - 35230 Bourgbarré - FRANCE / tel: +33 (0)2 99 05 77 77 - fax: +33 (0)2 99 57 73 55

Entreprise dont le système qualité a été certifié ISO 9001 par Bureau Veritas Certification.

SAS au capital de 4 957 200 € - RCS Rennes B 402 853 220 - Siret : 402 853 220 000 34 - APE : 1622 Z - n° TVA : FR 0640 2853220

www.panaget.com