



Daylight whites



N° 1000299

## FRENCH OAK AUTHENTIC LINEN, DIVA 139 CLICK / 12 MM

### Characteristics

**Specie:** French oak **Origin:** France

**Grade: Authentic** - Light and dark wood, black knots, filled knots, partially opened knots, traces of discolouration, black marks, cracks. This size of the knots is proportional to the width of the planks.

**Finish: Linen** - brushed, light white matt lacquered / Ecostrong matt lacquer - Gloss: 4/6

While we take the greatest care in manufacturing our flooring, there can sometimes be slight variations in colouring. So it's important to factor in margin 2-5% more than the actual you're covering. This means you won't run out of planks and will be sure to enjoy beautiful finished product. 시시

### Design

Engineered wide single plank made under the patent EN 13489  
Click made under Unilin patent n°EP1640530



### Description

**Width:** 139 mm  
**Length:** 495 to 1992 mm  
**Thickness:** 12 mm  
**Top layer:** 2.5 mm  
**Core:** HDF\*  
**Counterbalance:** unrolled wood  
**Profile:** 4 bevels

\*High Density Fiber board

### Packaging

**sqm/pack:** 1.38  
**Pack/pallet:** 65  
**sqm/pallet:** 89.70  
**Weight/sqm:** 9.9 kg  
**Weight/pallet:** 888.0 kg



### Installation method



Glue-free floating under the patent DTU 51.11





Glue down installation under the patent DTU 51.2



Floating installation using plastic DM and Isol 20 or fully glue down using Presto PM



Fully glue down Presto PM



# DECLARATION OF PERFORMANCE

N° 1000299



**Unique identification code of product-type:** Diva 139 Click, 12 mm, French oak

**Intended use/es:** Engineered single plank made under the patent EN 13489

Glue-free floating under the patent DTU 51.11

**Manufacturer:** PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

**System/s of Assessment and Verification of Constancy of Performance:** n°4

**Harmonised standard:** EN 14342 : 2013

## Declared performances:

Essential features	Performances	Appropriate Technical Documentation and/or Specific Technical Documentation	
Reaction of fire	Dfl-s1	EN 14342 : 2013	
Features for this classification: - Average minimum density (Kg/m <sup>3</sup> ) - Average thickness (mm) - Intended use, fitting mode	500 12 Floating fit		
Formaldehyde emission	E1		EN 717-1
Content of pentachlorophenol	PCP ≤ 5 ppm		-
Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree No DEVP0910046A)	Class A+ < 1µg/m <sup>3</sup>	ISO 16000	
Breaking strength	N/A	-	
Slipperiness	N/A	-	
Thermal conductivity (W/m.K)	0.15	EN 14342 / Chapter 4.7	
Thermal resistance (m <sup>2</sup> .K/W)	0.080		
Biological sustainability	Class 1	EN 335	
RE2020 - Building Carbon Index	3 kg.CO <sub>2</sub> /m <sup>2</sup>	-	
FDES 2022 - Life Cycle impact assessment	8.6 kg éq. CO <sub>2</sub> /m <sup>2</sup>	-	

N/A : Not Applicate

\*VOC: Volatile Organic Compounds

\*\*CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category.

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011 under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole FRANÇOIS - Executive Director

Bourgbarré, January 27th 2025

**Carole FRANÇOIS**

