



Daylight whites

## FRENCH OAK ZENITUDE LINEN, DIVA 184 CLICK / 12 MM

### Characteristics

#### Specie: French oak Origin: France

Grade: Zenitude - Light and dark wood, black knots, filled knots, partially opened knots, traces of discolouration, cracks, splits, heartwood, sapwood. Grade with all peculiarities of the wood without limitation. The size of the knots is proportional to the width of the planks.

**Finish: Linen** - brushed, light white matt lacquered / Ecostrong matt lacquer - Gloss: 4/6 While we take the greatest care in manufacturing our flooring, there can sometimes be slight variations in colouring. So it's important to factor in margin 2-5% more than the actual you're covering. This means you won't run out of planks and will be sure to enjoy beautiful finished product.^|A|

#### Design

Engineered extra-wide single plank made under the patent EN 13489 Click made under Unilin patent n°EP1640530



#### Description

Width: 184 mm Length: 495 to 1992 mm Thickness: 12 mm Top layer: 2.5 mm Core: HDF\* Counterbalance: unrolled wood Profile: 4 bevels High Density Fiber board

## Packaging

sqm/pack: 2.20 Pack/pallet: 40 sqm/pallet: 88.00 Weight/sqm: 9.9 kg Weight/pallet: 871.2 kg



### Installation method



Glue-free floating under the patent DTU 51.11



Floating installation using plastic DM and Isol 20 or fully glue down using Presto PM



Glue down installation under the patent DTU 51.2




Fully glue down Presto PM











PANAGET - 3 rue d'Orgères - 35230 Bourgbarré - FRANCE tel: +33 (0)2 99 05 77 77 // fax: +33 (0)2 99 57 73 55 // **www.panaget.com** 

N° 1007320



# **DECLARATION OF PERFORMANCE** N° 1007320

# CE

Unique identification code of product-type: Diva 184 Click, 12 mm, French oak Intented use/es: Engineered single plank made under the patent EN 13489 Glue-free floating under the patent DTU 51.11

Manufacturer: PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE System/s of Assessment and Verification of Constancy of Performance: n°4 Harmonised standard: EN 14342 : 2013

#### **Declared performances:**

Essential features	Performances	Appropriate Technical Documentation and/or Specific Technical Documentation
Reaction of fire	Dfl-s1	
Features for this classification:		
- Average minimum density (Kg/m³)	500	EN 14342 : 2013
- Average thickness (mm)	12	
- Intented use, fitting mode	Floating fit	
Formaldehyde emission	E1	EN 717-1
Content of pentachlorophenol	PCP ≤ 5 ppm	-
Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree No DEVP0910046A)	Class A+ < 1µg/m³	ISO 16000
Breaking strength	N/A	-
Slipperiness	N/A	-
Thermal conductivity (W/m.K)	0.15	EN 14342 / Chapter 4.7
Thermal resistance (m².K/W)	0.080	
Biological sustainability	Class 1	EN 335
RE2020 - Building Carbon Index	3 kg.CO <sub>2</sub> /m <sup>2</sup>	-
FDES 2022 - Life Cycle impact assessment	8.6 kg éq. CO <sub>2</sub> /m <sup>2</sup>	-

N/A : Not Applicate

\*VOC: Volatile Organic Compounds

\*\*CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category.

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011 under the sole responsability of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole FRANÇOIS - Executive Director

Bourgbarré, January 27th 2025 Carole FRANÇOIS

0

3 rue d'Orgères - 35230 Bourgbarré - FRANCE / tel: +33 (0)2 99 05 77 77 - fax: +33 (0)2 99 57 73 55 Entreprise dont le système qualité a été **certifié ISO 9001** par Bureau Veritas Certification. SAS au capital de 4 957 200 € - RCS Rennes B 402 853 220 - Siret : 402 853 220 000 34 - APE : 1622 Z - n° TVA : FR 0640 2853220 www.panaget.com