



Elegant browns

N° 1019563

FRENCH OAK INTENSO CUIR, ORFEO 139 CLICK / 14 MM

Charateristics

Specie: French oak **Origin :** France

Grade: Intenso - Light and dark wood, black knots, filled knots, partially opened knots, discolouration, cracks, sapwood, bluish sapwood.
Grade with all the peculiarities of the wood.

Finish: Cuir - brushed, old leather-tone matt oiled / Oil - Brillance (gloss) : 4/8

For oiled wood floors, apply a thin coat of Panaget maintenance oil right after installation. Please refer to our maintenance guide.

Design

Engineered double plank in fixed lengths made under patent EN 13489
Click made under Unilin patent n°EP1640534



Description

Width: 139 mm
Length: 1500 mm
Thickness: 14 mm
Top layer: 3,4 mm
Core: HDF*
Couterbalance: unrolled wood
Profile: square edged

*High Density Fiber board

Packaging

sqm/pack: 1,46
Pack/pallet: 50
sqm/pallet: 73,00
Weight/sqm: 11,8 kg
Weight/pallet: 861,4 kg



if installation and maintenance rules are followed

Class of use:
31 R2



Installation method



Glue-free floating under the patent DTU 51.11




Glue down installation under the patent DTU 51.2




Floating installation using plastic DM and Isol 20 or fully glue down using Presto PM



Fully glue down Presto PM



*Emissions of volatile substances which could be toxic if inhaled. These are rated on scale from A+ (very low) to C (high).



PANAGET - 3 rue d'Orgères - 35230 Bourgarré - FRANCE
tel: +33 (0)2 99 05 77 77 // fax: +33 (0)2 99 57 73 55 // www.panaget.com



DECLARATION OF PERFORMANCE

N° 1019563

Unique identification code of product-type: ORFEO 139 Click, 14 mm, French oak

Intended use/es: Engineered single plank made under the patent EN 13489

Glue-free floating under the patent DTU 51.11

Manufacturer: PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

System/s of Assessment and Verification of Constancy of Performance: n°4

Harmonised standard: EN 14342 : 2013

Declared performances:

Essential features	Performances	Appropriate Technical Documentation and/or Specific Technical Documentation	
Reaction of fire	Dfl-s1	EN 14342 : 2013	
Features for this classification: - Average minimum density (Kg/m3) - Average thickness (mm) - Intended use, fitting mode	500 14 Floating fit		
Formaldehyde emission	E1		EN 717-1
Content of pentachlorophenol	PCP ≤ 5 ppm		-
Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree No DEVP0910046A)	Classe A+ < 1µg/m ³	ISO 16000	
Breaking strengthe	NPD	-	
Slipperiness	NPD	-	
Thermal conductivity (W/m.K)	0,15	EN 14342 / Chapter 4.7	
Thermal resistance (m2.K/W)	0,093		
Biological sustainability	Class 1	EN 335	
RE2020 - Building Carbon Index	3 kg.CO ₂ /m ²	-	
FDES 2022 - Life Cycle impact assessment	8,6kg éq. CO ₂ /m ²	-	

N/A : Not Applicate

*VOC: Volatile Organic Compounds

**CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category.

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011 under the sole responsibility of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole FRANÇOIS - Executive Director

Bourgbarré, 14 January 2026
Carole FRANÇOIS