PANAGET
manufacture française de parquet
DEPUIS 1929

Timeless natural hues

N° 1021454

FLAMED BEECH BOIS FLOTTÉ, HERRINGBONE 139 TONGUE&GROOVE / 14 MM

Charateristics

Specie: Flamed beech **Origin :** France

Grade: - Flamed red wood, light and dark wood, knots, all pecularities accepted

Finish: Bois flotté - brushed, matt lacquered with unfinished aspect / Matt lacquer - Brillance (gloss) : 4/6

Design

Engineered single plank herringbone pattern made under patent EN 13489
Tongue & Groove

Description

Width: 139 mm
Length: 800 mm
Thickness: 14 mm
Top layer: 3,4 mm
Core: plywood
Couterbalance: unrolled wood
Profile: 4 bevels

Packaging

sqm/pack: 2,22
Pack/pallet: 32
sqm/pallet: 71,04
Weight/sqm: 7,4 kg
Weight/pallet: 525,7 kg

if installation and maintenance rules are followed

Class of use:

31 R2



Installation method

Floating glued installation under the patent DTU 51.11

Glue down installation under the patent DTU 51.2

Fully glue down using our special Presto PM glue.



*Emissions of volatile substances which could be toxic if inhabited. These are rated on scale from A+ (very low) to C (high).

Registration, Evaluation, Authorisation of Chemicals.

PANAGET - 3 rue d'Orgères - 35230 Bourgbarré - FRANCE
tel: +33 (0)2 99 05 77 77 // fax: +33 (0)2 99 57 73 55 // **www.panaget.com**

PANAGET
manufacture française de parquet
DEPUIS 1929

DECLARATION OF PERFORMANCE

N° 1021454

CE

Unique identification code of product-type: HERRINGBONE 139 Tongue&Groove, 14 mm, Flamed beech

Intented use/es: Engineered single plank made under the patent EN 13489

Floating glued installation under the patent DTU 51.11

Manufacturer: PANAGET - 3 rue d'Orgères 35230 Bourgbarré / FRANCE

System/s of Assessment and Verification of Constancy of Performance: n°4

Harmonised standard: EN 14342 : 2013

Declared performances:

Essential features	**Performances**	**Appropriate Technical Documentation and/or Specific Technical Documentation**
Reaction of fire	Dfl-s1	EN 14342 : 2013
Features for this classification: - Average minimum density (Kg/m3) - Average thickness (mm) - Intented use, fitting mode	 500 14 Floating fit	
Formaldehyde emission	E1	EN 717-1
Content of pentachlorophenol	PCP ≤ 5 ppm	-
Release of other dangerous substances: - VOC* emissions (Decree No 2011-321) - CMR 1&2** emissions (Decree No DEVP0910046A)	 Classe A+ < 1µg/m³	ISO 16000
Breaking strengthe	NPD	-
Slipperiness	NPD	-
Thermal conductivity (W/m.K)	0,13	EN 14342 / Chapter 4.7
Thermal resistance (m2.K/W)	0,108	
Biological sustainability	Class 1	EN 335
RE2020 - Building Carbon Index	3 kg.CO_2/m²	-
FDES 2022 - Life Cycle impact assessment	8,6kg éq. CO_2/m²	-

N/A : Not Applicate
**VOC: Volatile Organic Compounds*
***CMR 1&2: Carcinogenics, Mutagens or Reproductive toxin of 1&2 category.*

The performances of product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011 under the sole responsability of the manufacturer identified above.

Signed for and behalf of the manufacturer by: Carole FRANÇOIS - Executive Director

Bourgbarré, 14 January 2026
Carole FRANÇOIS

3 rue d'Orgères - 35230 Bourgbarré - FRANCE / tel: +33 (0)2 99 05 77 77 - fax: +33 (0)2 99 57 73 55
Entreprise dont le système qualité a été **certifié ISO 9001** par Bureau Veritas Certification.
SAS au capital de 4 957 200 € - RCS Rennes B 402 853 220 - Siret : 402 853 220 000 34 - APE : 1622 Z - n° TVA : FR 0640 2853220
www.panaget.com